

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 12308-6 (1991): Methods for Chemical Analysis of Cast Iron and Pig Iron, Part 6: Determination of silicon by gravimetric method (for silicon 0.1 to 6.0 percent) [MTD 6: Pig iron and Cast Iron]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



भारतीय मानक
ढलवां लोहे एवं कच्चे लोहे के रासायनिक
विश्लेषण की पद्धतियाँ

भाग 6 भारात्मक पद्धति द्वारा सिलिकॉन ज्ञात करना
(0.1 से 6.0 प्रतिशत सिलिकॉन के लिए)

Indian Standard

**METHODS FOR CHEMICAL ANALYSIS OF
CAST IRON AND PIG IRON**

**PART 6 DETERMINATION OF SILICON BY GRAVIMETRIC METHOD
(FOR SILICON 0.1 TO 6.0 PERCENT)**

UDC 669.162.275.12 + 669.13 : 543 [546.28]

© BIS 1991

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

FOREWORD

This Indian Standard (Part 6) was adopted by the Bureau of Indian Standards, after the draft finalized by the Methods of Chemical Analysis of Ferrous Metals Sectional Committee had been approved by the Metallurgical Engineering Division Council.

Chemical analysis of cast iron and pig iron was covered in IS 228 : 1959 'Methods of Chemical analysis of pig iron, cast iron and plain carbon and low alloy steels (*revised*)'. During its second revision it was decided that a comprehensive series should be prepared for chemical analysis of all type of steels and the other covering the chemical analysis of cast iron and pig iron. Accordingly IS 228 on revision was published in several parts covering chemical analysis of various steels only and a separate series of standards under IS 12308 is being published for chemical analysis of cast iron and pig iron. This standard (Part 6) is one in the latter series. The other parts in the series are as follows:

IS 12308 Methods for chemical analysis of cast iron and pig iron:

- Part 1 Determination of total carbon by thermal conductivity method
- Part 2 Determination of sulphur by iodimetric titration method
- Part 3 Determination of manganese by periodate spectrophotometric method
- Part 4 Determination of total carbon, graphitic carbon and combined carbon by gravimetric method
- Part 5 Determination of phosphorus by alkalimetric method (for phosphorus 0.01 to 0.50 percent)
- Part 7 Determination of nickel by dimethylglyoxime (gravimetric) method (for nickel 0.5 to 36 percent)
- Part 8 Determination of chromium by persulphate (oxidation) method (for chromium 0.1 to 28 percent)
- Part 9 Determination of molybdenum by thiocyanate (spectrophotometric) Method (for molybdenum 0.1 to 1.0 percent)
- Part 10 Determination of manganese (up to 7.0 percent) by arsenite (volumetric) method
- Part 11 Determination of total carbon by the direct combustion (volumetric) method (for carbon 1.50 to 4.50 percent)

The method given in this part for determination of silicon has been updated on the basis of experience gained during the past, while following the method of test given in 6 of IS 228 : 1959 for cast iron and pig iron.

In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated is to be rounded off, it shall be done in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'.

Indian Standard

METHODS FOR CHEMICAL ANALYSIS OF CAST IRON AND PIG IRON

PART 6 DETERMINATION OF SILICON BY GRAVIMETRIC METHOD (FOR SILICON 0.1 TO 6.0 PERCENT)

1 SCOPE

This standard (Part 6) describes the gravimetric method for determination of silicon in the range of 0.1 to 6.0 percent in cast iron and pig iron.

2 SAMPLING

The sample shall be drawn and prepared as prescribed in the relevant Indian Standard.

3 QUALITY OF REAGENTS

Unless specified otherwise, analytical grade reagents and distilled water (*see* IS 1070 : 1977) shall be employed in the test.

4 DETERMINATION OF SILICON BY GRAVIMETRIC METHOD

4.1 Outline of the Method

Sample is dissolved, silicic acid is dehydrated and silica is determined after hydrofluorization.

4.2 Reagents

4.2.1 Dilute Nitric Acid — 2:3 (*v/v*) and 1:2 (*v/v*).

4.2.2 Dilute Hydrochloric Acid — 1:1 (*v/v*).

4.2.3 Perchloric Acid — 70 percent (*v/v*).

4.2.4 Tartaric Acid — 20 percent (*m/v*).

4.2.5 Dilute Sulphuric Acid — 20 percent (*v/v*).

4.2.6 Hydrofluoric Acid — 40 percent (*v/v*).

4.3 Procedure

4.3.1 Transfer 0.500 to 2.000 g of sample (depending upon the silicon content) to a 400-ml tall-form beaker covered with a watch glass and dissolve in 20 ml of nitric acid (2:3 *see* 4.2.1). When the violent reaction has ceased, add 20 ml of dilute hydrochloric acid (1:1 *see* 4.2.2). Heat for a minute or so. Cool and add 20 ml perchloric acid. Evaporate the solution to fumes for 15 to 20 minutes at such a rate that the perchloric acid refluxes on the sides of the beaker.

4.3.2 Cool the solution and add 100 ml of hot water (40 to 50°C), boil gently for two to three minutes till the iron salts dissolve.

NOTE — If the sample portion contains chromium (more than 100 mg) add 1 ml of tartaric acid solution for each 25 mg of chromium.

4.3.3 Add paper pulp to the solution and filter through medium textured filter paper, being careful to remove adhering particles from the beaker by rubber tipped glass rod. Wash the residue thoroughly with hot dilute hydrochloric acid (1:1) and finally with hot water (5-6 times) till free from chloride.

NOTE — Test the filtrate with 0.5 percent silver nitrate solution.

4.3.4 Transfer the residue and the paper in a platinum crucible. Heat at 600°C until the carbon is oxidized. Finally ignite the residue at 1 000 to 1 050°C for 30 minutes, cool in a desiccator and weigh (M_1).

4.3.5 Add sufficient dilute sulphuric acid (*see* 4.2.5) to moisten the residue and then add 5 to 10 ml of hydrofluoric acid. Evaporate to dryness and then heat gradually until sulphuric acid is removed. Ignite at 1 000 to 1 050°C for 5 to 10 minutes, cool in a desiccator and weigh (M_2).

4.3.6 Carry out a blank determination, following the same procedure as specified in 4.3.1 to 4.3.5 and using the same amount of reagents.

4.4 Calculation

$$\text{Silicon, percent by mass} = \frac{(A - B) \times 46.72}{C}$$

where

$A = (M_1 - M_2)$ = mass, in g, of silica obtained from the sample,

B = mass, in g, of silica obtained from the blank, and

C = mass, in g, of sample taken.

4.5 Reproducibility

±0.002 at 0.2 percent Silicon,

±0.01 at 4 percent Silicon, and

±0.02 at 6 percent Silicon.

Standard Mark

The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference :

Doc : No. MTD 2 (3263)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha
(Common to all Offices)

Regional Offices :

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg
NEW DELHI 110002

Telephone

{ 331 01 31
{ 331 13 75

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola
CALCUTTA 700054

37 86 62

Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036

53 38 43

Southern : C.I.T. Campus, IV Cross Road, MADRAS 600113

235021 6

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)
BOMBAY 400093

6 32 92 95

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI.
HYDERABAD. JAIPUR. KANPUR. PATNA. THIRUVANANTHAPURAM.